

GEODESMO -50**Product Data Sheet****Low viscosity, fast curing, polyurethane based all-purpose primer** **Description**

GEODESMO-50 is a one-component product, fast curing polyurethane based primer suitable for all substrates. It can be used successfully on both porous and non-porous substrates.

It is very similar in viscosity and wetting ability as **MICROSEALER-50** but has an increased curing speed (same day primer) which allows it to be used more successfully in colder climates and when rain is not very predictable. It is the preferred option in cases of extreme porosity in concrete surfaces where multiple coats of **MICROSEALER-50** may be required. Additionally, it can be effectively used on both dry and wet concrete, even green concrete, not only as primer but also as a low-cost sealing solution, increasing, thus, the durability of the substrate.

 **Features & Benefits**

- One component
- Fast curing
- Low viscosity
- Easily applied, even on wet concrete
- Excellent wetting, impregnation and paint-over time
- Elastic

 **Recommended For**

To be used as primer for:

- Humid, damp or wet concrete,
- Faster curing version of **MICROSEALER-50**

 **Application Procedure**

Clean the surface using a high-pressure washer, if possible. Remove oil, grease and wax contaminants. Cement laitance, loose particles, mould release agents, cured membranes must also be removed.

- ✓ **Thinning:** In order to reduce the chance of bubble formation and to help keep consumption below 500 gr/m².
- ✓ **Application:** Apply with brush or roller. Once cured, the main membrane (e.g. **HYPERDESMO**[®] System) can be applied.

 **Compliance**


CE certified according ETAG 005 (parts 1 & 6) and ETAG 033 as part of various **HYPERDESMO**[®] Systems.

 **Shelf Life**


Can be kept for 12 months minimum in the original unopened pails in dry places and at temperatures of 5-25 °C. Once opened, use as soon as possible

 **Packaging**

1 lt, 4 lt, 20 lt and drums.

 **Consumption**

Concrete: 100-500 gr/m², subject to substrate porosity.

 **Cleaning**

Due to the very high strength of adhesion of **GEODESMO-50**, avoid staining surrounding areas. Clean tools and equipment first with paper and then using **SOLVENT-01**. Rollers will not be re-usable.

 **Safety Information**

GEODESMO-50 contains solvents. Apply in well-ventilated, no smoking areas, away from naked flames. In closed spaces use ventilators and carbon active masks. The M.S.D.S. (Material Safety Data Sheet) is available on request.

 **Limitations**

Will discolor when used on its own exposed. This is purely visual and does not affect the performance of the membrane.

GEODESMO -50

Product Data Sheet


Technical Specifications

In liquid form (before application):

Property	Units	Method	Specification
Viscosity (Brookfield)	cP	ASTM D2196-86 @ 25 °C	60-100
Specific weight	gr/cm ³	ASTM D1475 / DIN 53217 / ISO 2811, @ 20 °C	0.9-1.00

In cured form (after application):

Property	Units	Method	Specification
Tensile strength at break @ 23 °C	N/mm ²	ASTM D412 / EN-ISO-527-3	35
Elongation @ 23 °C	%	ASTM D412 / EN-ISO-527-3	> 150
Application of main membrane	hours	-	2-24
Adhesion to cement	MPa	ASTM D1640	> 4
Adhesion of HYPERDESMO® to GEODESMO PRIMER	MPa	ASTM D1640	> 5
Dry to touch: On DRY cement On WET cement	hours	-	1-2 1

For more information on Hyperdesmo, Hyperseal & Aquasmart range of products and application methods
Please contact Alchimica Technical Service at info@alchimica.co.in

NONE OF OUR PUBLISHED INSTRUCTIONS AND SPECIFICATIONS, IN WRITING OR OTHERWISE, ARE BINDING EITHER IN GENERAL OR WITH RESPECT TO ANY THIRD PARTY RIGHTS, OR DO THEY RELIEVE INTERESTED PARTIES OF THEIR DUTY TO SUBJECT THE PRODUCT TO AN ADEQUATE EXAMINATION OF ITS SUITABILITY. IN NO EVENT WILL ALCHIMICA BE RESPONSIBLE FOR DAMAGES OF ANY NATURE, WHATSOEVER, RESULTING FROM THE USE OF OR RELIANCE UPON INFORMATION OR THE PRODUCT TO WHICH INFORMATION REFERS.

Alchimica India Private Limited

No, 51, G Alwarthirunagar Annexe 1st Main Road
Valasarvakkam, Chennai - 600087.

Headquarters

7, Lampsakou St,
115 28 Athens, Greece.

R&D / Plant

13, Oryzomylon St,
122 44 Aegaleo, Greece.


**25 YEARS
EXPECTED
WORKING LIFE**
