

HYPERDESMO®-S-WR**Product Data Sheet****Polyurethane Liquid Membrane For Waterproofing Of Wet Rooms And Non-exposed Applications.** **Description**

HYPERDESMO®-S-WR is a result of **ALCHIMICA's** investment in new production facilities and polymerization procedures. This investment facilitated the manufacture of a low solvent **HYPERDESMO®** i.e. it is not subject to ADR regulation and can be transported as non-flammable material without hazardous transportation limitations (non-IMO).

The product is a one component polyurethane fluid that cures with the humidity in the atmosphere. It produces a highly elastic, hydrophobic membrane and has been designed to offer excellent long-term waterproofing of wet rooms, substructures and any application not exposed to UV. The rheology of the material is such that it allows easy application even on vertical substrates.

The use of **HYPERDESMO®** range additives is possible: ACCELERATOR-3000A or SOLVENT-01.

Full range of primers used in classic **HYPERDESMO®** system applies to **HYPERDESMO®-S-WR** as well.

 **Recommended For**

Waterproofing of:

- Wet rooms
- Foundation walls
- Flat roofs (under tiles or screed)
- Verandas and balconies (under protection)

 **Compliance**

The product is **CE certified**: 2085-CPR-061 according to the European Standard **EN 1504-2**.

 **Features & Benefits**

- Highly Elastic.
- Easy application even on vertical substrates.
- Resistance to cold: The film remains elastic even down to -40°C.
- Non-toxic after full cure.
- Water vapor transmission: The film breathes, so there is no accumulation of humidity under the coat.
- Special primers available for almost any substrate.

 **Limitations**

Not recommended for

- Applications where high temperatures are expected. Not recommended for waterproofing under dark color tiles (outdoors) or on thermo-insulating materials.
- Unsound substrates.
- Waterproofing of swimming pool surfaces in contact with chemically treated water.
- UV exposure

HYPERDESMO®-S-WR

Product Data Sheet

Application Prerequisites

- ✓ **Can be successfully applied on:** Concrete/steel reinforced concrete or otherwise, fibrous cement, mosaic, cement roof tiles, wood, corroded metal, and galvanized steel. For information about other substrates, please contact our tech department.
- ✓ **Standard concrete substrate conditions (no primer needed):**
 - Hardness: $R_{28} = 15 \text{ MPa}$
 - Humidity: $W < 10\%$
 - Temperature: $5\text{-}35^\circ\text{C}$
 - Relative humidity: $< 85\%$
- ✓ **Primer selection for special conditions and substrates:** Please refer to the **Primer Selection Table**.

Application Procedure

Clean the substrate using a high-pressure washer, if possible. Remove oil, grease and wax contaminants. Cement laitance, loose particles, mould release agents, cured membranes must also be removed. Surface irregularities should also be filled with **HYPERSEAL®-25LM-S** or **HYPERSEAL®-EXPERT**.

- ✓ **Priming:** Apply the required primer following the guidelines above.
- ✓ **Mixing:** Use a low speed (300 rpm) mixer. Add SOLVENT-01 at 5-10% for application by spraying.
- ✓ **Application:** Apply with roller, brush or airless spraying (200-250 bar) in two, at least, coats.. Do not exceed 48 hours between coats.

Shelf Life

Can be kept for 12 months minimum in the original unopened pails in dry places and at temperatures of $5\text{-}25^\circ\text{C}$. Once opened, use as soon as possible.

Consumption

Minimum total consumption: **1.5 kg/m²** in one or two coats

Cleaning

Clean tools and equipment first with paper and then using SOLVENT-01. Rollers will not be re-usable.

Safety Information

The MSDS (Material Safety Data Sheet) is available upon request.

Packaging

- 6 kg, 25 kg pails.
- Color : Black

Technical Specifications

In Liquid Form (Before application):

Property	Units	Method	Specification
Viscosity (Brookfield)	cP	ASTM D2196-86, @ 25°C	3,000-6,000
Specific weight	gr/cm ³	ASTM D1475 / DIN 53217 / ISO 2811, @ 20°C	1.5-1.6

HYPERDESMO®-S-WR

Product Data Sheet

In Cured Form (After application):

Property	Units	Method	Specification
Service temperature	°C	-	-40 to 60
Hardness	Shore A	ASTM D2240/DIN 53505 / ISO R868	60
Tensile strength at break @ 23°C	N/mm ²	ASTM D412 / EN-ISO-527-3	3.0
Elongation @ 23°C	%	ASTM D412 / EN-ISO-527-3	>1000
Water vapor transmission	gr/m ² .hr	ASTM E96 (Water Method)	0.8


DOP: 2085-CPR-061/07.12.2018
EN 1504-2
Surface Protection Products – Coating

Permeability to CO ₂	SD>50 m
Permeability to water vapor	SD<5 m Class I (permeable)
Capillary absorption & permeability to water	W<0.1 kg/m ² .0.5h
Adhesion strength by pull-off test	≥1.5 (1.0) N/mm ²
Adhesion strength after thermal compatibility	≥1.5 (1.0) N/mm ²
Reaction to fire	Euroclass F
Dangerous substances	In accordance with 5.3
Artificial weathering according to EN 1062-11, for outside application	No change
-blistering	
-cracking	
-flaking	
-colour change	

For more information on Hyperdesmo, Aquasmart & Hyperseal range of products and application methods

 Please contact Alchimica Technical Service at info@alchimica.co.in

NONE OF OUR PUBLISHED INSTRUCTIONS AND SPECIFICATIONS, IN WRITING OR OTHERWISE, ARE BINDING EITHER IN GENERAL OR WITH RESPECT TO ANY THIRD PARTY RIGHTS, OR DO THEY RELIEVE INTERESTED PARTIES OF THEIR DUTY TO SUBJECT THE PRODUCT TO AN ADEQUATE EXAMINATION OF ITS SUITABILITY. IN NO EVENT WILL ALCHIMICA BE RESPONSIBLE FOR DAMAGES OF ANY NATURE, WHATSOEVER, RESULTING FROM THE USE OF OR RELIANCE UPON INFORMATION OR THE PRODUCT TO WHICH INFORMATION REFERS.

Alchimica India Private Limited

 No, 51, G Alwarthirunagar Annexe 1st Main Road
 Valasarvakkam, Chennai - 600087.

Headquarters

 7, Lampsakou St,
 115 28 Athens, Greece.

R&D / Plant

 13, Oryzomylon St,
 122 44 Aegaleo, Greece.


**25 YEARS
 EXPECTED
 WORKING LIFE**
