

HYPERSEAL®-EXPERT-150

Product Data Sheet

**One Component, Polyurethane-based, Low Modulus Joint Sealant
Ideal For Use In High Humidity Conditions** **Description**

HYPERSEAL®-EXPERT-150 is a novel low modulus expansion joint sealant, especially formulated to ensure bubble free cure even at very high temperature and humidity climatic conditions. The product displays excellent thixotropy allowing its use even in very large expansion joints.

It cures by reaction with atmospheric humidity to produce a joint sealant with a **50% joint movement accommodation factor** and excellent adhesion on substrates traditionally problematic for PU sealants, e.g. glass, aluminum, steel, polycarbonate, etc. The extrusion rate and tooling of the sealant remain the same throughout a very wide range of temperature and humidity conditions.

 **Compliance**

- ISO-11600,
- Type F - class: 25LM,
- DIN-18540-F,
- ASTM C920,
- U.S. Federal Specification TT-S-00230C,
- Type II Class A.

HYPERSEAL®-EXPERT is **CE certified** according to **EN 15651-1** (Sealants for Facades) and **15651-4** (Sealants for Floor Joints with Foot traffic).

 **Recommended For**

Sealing of joints in:

- In-situ concrete,
- Precast concrete panels,
- Brick and block work,
- water tanks and swimming pools,
- metal frames,
- aluminum windows and panels,
- irrigation channels,
- glass,
- granite & marble.

 **Features & Benefits**

- No bubbling / swelling upon curing in difficult climatic conditions
- Excellent Thixotropy
- Excellent adhesion on almost any type of surface, with or without the use of special primers
- Excellent extrusion, tooling and storage stability over wide range of climatic conditions
- Low modulus, joint movement accommodation 50%
- Microorganism and fungus resistant
- Excellent heat resistance, suitable for application where exposure to temperatures >60°C take place
- Resistance to cold: The sealant remains elastic even down to -40°C
- Excellent chemical resistance, suitable for sealing joints in swimming pools and chemically treated water.

 **Limitations**

- Not recommended for direct application on unsound substrates.
- In this case, the substrate must be primed with **MICROPRIMER-PU**, which will re-enforce the concrete and produce a strong durable substrate for sealant application.
- Highly porous substrates, dusty surfaces or poorly compacted concrete, must have their porous bond area surfaces thoroughly sealed to avoid the possibility of air bubbles being blown into the uncured sealant if the substrate temperature rises.
- **HYPERSEAL®-EXPERT-150** is suitable for UV exposure and has been certified for external use according to **EN 15651-1 & 4**, however if colour retention and no chalking is required, it is recommended that the sealant be painted with good quality acrylic paint.

HYPERSEAL®-EXPERT-150

Product Data Sheet

Application Procedure

- ✓ Clean joint thoroughly, and ensure that no oil, grease and wax contaminants, silicone remains are present.
- ✓ For many applications, primer is not required. In the case of application on very porous substrates, bond area surfaces thoroughly to avoid the possibility of air bubbles being blown into the uncured sealant if the substrate temperature rises. The recommended primer is **MICROPRIMER-PU**.
- ✓ Apply backing material such as open cell polyurethane or a closed cell polyethylene backing rod. Although both types of backing rod are recommended, care must be taken when using the closed cell polyethylene rod that the outer skin not be punctured as in rising temperature conditions it may cause bubbling. Backing rod application is important as it ensures that the correct width to depth ratio is achieved to provide a firm backing against which the sealant can be tooled off.
- ✓ Slide the sealant into the applicator gun, cut off the very end of the sealant packaging and fit the gun with the nozzle that has been cut to deliver the right bead size
- ✓ Extrude the sealant into the joint ensuring that no air is trapped in the joint.
- ✓ Tooling is recommended immediately after the application of sealant
- ✓ The ratio width to depth should be 2:1 subject to a minimum depth of 10mm

Packaging

- 600cc sausage
- 300cc cartridge

Shelf Life

12 months minimum for 600 cc sausages and 9 months for 300 cc cartridges in the original packaging when stored in dry places and at temperatures of 5-25°C. Once opened, use as soon as possible.

Consumption

Linear meters per 600cc sausage:

WIDTH \ DEPTH	5 mm	10 mm	15 mm	20 mm	25 mm
5 mm	24	12			
10 mm			4	3	2.4
15 mm					1.6

Technical Specifications

Property	Units	Method	Specification
Specific weight	gr/cm ³	ASTM D1475 / DIN 53217 / ISO 2811, @ 20 °C	+/- 1.49
Tack free time, @ 25 °C & 55% RH	hours	-	2.5-3.5
Cure Rate	mm/day	-	2-3
Service temperature	°C	-	-40 to 80
Hardness	Shore A	ASTM D2240 / DIN 53505 / ISO R868	±27
Modulus at 100% elongation	N/mm ²	ASTM D412 / EN-ISO-527-3	0.3
Elongation	%	ASTM D412 / EN-ISO-527-3	>700
Thermal Resistance (100 days, 80°C)	-	EOTA TR011	Passed
Toxicity	-	-	No restrictions after full cure
Resilience	%	DIN 52458	>90
Hydrolysis (8% KOH, 15 days @ 50°C)	-	-	No elastomeric property change
Hydrolysis (H ₂ O, 30 days-cycle 60-100°C)	-	-	No elastomeric property change
HCl (PH=2, 10 days @RT)	-	-	No elastomeric property change
Adhesion to concrete	N/mm ²	ASTM D4541	> 2
QUV Accelerated Weathering Test	-	ASTM G53	Passed (after 2000hr)

HYPERSEAL®-EXPERT-150

Product Data Sheet

EU-Declaration of Performance:

In accordance with Annex III of Regulation (EU) No.305/2011
(Construction Product Regulation)

For the product "HYPERSEAL® EXPERT"

No: CPR-5113/850/14-3

CPR-5113/850/14-4.

The notified body (0761):

Materiaiorufarsai (MPA)
fur das Bauwesen BeethovenstratBe 52
D-38106 Braunschweig

EN 15651 – part 1 & part 4

The product is used as a single-component, polyurethane-based joint sealant for façade elements and for walkways.

Essential characteristics	Performance	Harmonized technical specification
Reaction to fire	Class E	EN ISO 11925-2
Elastic recovery (%)	>70%	EN ISO 7389
Resistance to flow (mm)	≤3mm	EN ISO 7390
Tensile properties – secant modulus- at 23°C	≤0.4MPa	EN ISO 8339
Tensile properties – secant modulus- at -30°C	≤0.9MPa	EN ISO 8339
Tensile properties at maintained extension	NF	EN 8340
Adhesion/cohesion properties at variable temperature	NF	EN ISO 9047
Loss of mass/volume	≤10%	EN ISO 10563
Tensile properties at maintained extension after immersion in water (4 days)	NF	EN ISO 10590
Tensile strength (movement capacity 50%)	NF	EN ISO 8340

Outdoor Requirements:

Tensile properties at maintained extension after immersion in water (28 days)	NF	EN ISO 10590
Tensile properties at maintained extension after immersion in saltwater (28 days)	NF	EN ISO 10590
Adhesion/cohesion properties after exposure to heat, water and artificial light through glass	NF	EN ISO 11431

For more information Hyperseal range of products and application methods
Please contact Alchimica Technical Service at info@alchimica.co.in

NONE OF OUR PUBLISHED INSTRUCTIONS AND SPECIFICATIONS, IN WRITING OR OTHERWISE, ARE BINDING EITHER IN GENERAL OR WITH RESPECT TO ANY THIRD PARTY RIGHTS, OR DO THEY RELIEVE INTERESTED PARTIES OF THEIR DUTY TO SUBJECT THE PRODUCT TO AN ADEQUATE EXAMINATION OF ITS SUITABILITY. IN NO EVENT WILL ALCHIMICA BE RESPONSIBLE FOR DAMAGES OF ANY NATURE, WHATSOEVER, RESULTING FROM THE USE OF OR RELIANCE UPON INFORMATION OR THE PRODUCT TO WHICH INFORMATION REFERS.

Alchimica India Private Limited

No, 51, G Alwarthirunagar Annexe 1st Main Road
Valasarvakkam, Chennai - 600087.

Headquarters

7, Lampsakou St,
115 28 Athens, Greece.

R&D / Plant

13, Oryzomylon St,
122 44 Aegaleo, Greece.

CE 25 YEARS
EXPECTED
WORKING LIFE

